

# Smoking Maniac

## Smoking Maniac

Smoking Maniac Ltd.  
Smoking Maniac  
Варна  
9014 Варна  
Bulgaria  
+359 888 707276

# Smoking Maniac

## Резервни части за Кайфун мини V.3



Резервни части за изпарителя Кайфун мини версия 3 - комплект 9 рингове

Price with discount 5,00 лв

Price with discount 5,00 лв

Salesprice with discount

Sales price 6,00 лв

Discount

Tax amount 1,00 лв

[Ask a question about this product](#)

Manufacturer [Смокинг Маниак](#)

Резервни части за подмяна на изпарителя Кайфун мини версия 3. Пълен комплект от 9 рингове - 9 бр. Ринговете са NBR70 (Бутадиенакрилнитрилов каучук с търговско наименование - Perbunan) , маслостойчиви и не са китайски! Качеството е най доброто на българския пазар.



## Smoking Maniac

Smoking Maniac Ltd.  
Smoking Maniac  
Варна  
9014 Варна  
Bulgaria  
+359 888 707276



### Технически данни:

Количество: 9 бр.

Материал: NBR70

Размери: според техническите данни на производителя (Svoemesto)

Работна температура: -30 до +100 гр.

\*\*\*\*\*

**NBR** is the most common standard material because of its good mechanical properties and resistance to mineral oil-based lubricants and greases. Good resistance to fuels is usually possible only with special compounds.

Its properties are mainly determined by the acrylonitrile content (ACN between 18% and 50%). A low ACN content ensures good flexibility at low temperatures, but offers limited resistance to oils and fuels; as the ACN content increases, flexibility at low temperatures decreases and resistance to oils and fuels improves. The standard NBR material offers an average ACN content to suit a wide range of applications with balanced properties. It has good mechanical technological values such as high abrasion resistance, as well as good resistance to mineral oil-based lubricants and greases, hydraulic oils H, H-L, H-LP, non-inflammable hydraulic fluids HFA, HFB, HFC, aliphatic hydrocarbons, silicone oil and greases and water to approx. +80°C.

NBR is generally not resistant to aromatic and chlorinated hydrocarbons, fuels with a high aromatic content, polar solvents, glycol-based brake fluids, and non-inflammable hydraulic fluids HFD. It has a low resistance to ozone, weather and ageing, but in most applications, e.g. when the material is wetted with oil, this has no negative effect.

### Reviews

There are yet no reviews for this product.